




PREMIUM METALIZED SILVER PET THERMAL FILM

II PRODUCT DESCRIPTION

It is a BOPET based product with Silver metallic luster. The product is non-toxic and environmentally friendly, low level of static, consistent corona treatment, excellent resistance to tear & elongation, primarily used in the printing industry. The film accepts UV spot varnishing, foil stamping as well as screen printing.

II FEATURES

- Excellent printability
- Excellent silver metallic luster
- Excellent resistance to tear & elongation

II TECHNICAL DATA

PROPERTIES	TYPICAL VALUE	TEST METHOD
Thickness, mil	1.2	GB/T6672
Yield, m ² /kg	36.1	
Wetting Tension, mN/m		
BOPET surface:	≥38	GB/T14216
Adhesive surface:	≥48	
Heat Shrinkage, %		
MD	≤2.0	Q/CPKDX0001
TD	≥1.0	
Coefficient of Friction		
Outside / Outside	≤0.5	ASTM D1894

II APPLICATION TECHNOLOGY

Adjust the processing parameter according to the production job requirement.

Laminating Equipment : thermal laminating machine

Temperature : 95-120℃

Pressure : 8-18MPa

Speed : 10-70m/min

II STORAGE AND HANDLING

- Keep upright in a clean, dry and ventilated warehouse (T=5-30℃, H=20-60%); avoid storage in direct sunlight or near sources of heat less than 2m.
- In order to avoid damage to the film surface or end surface, avoid collision during product transportation, loading and unloading process.
- When using a thermal laminating film in winter, it should be placed in the production room in advance so that the temperature of the film is higher

KDX CHINA

ZHANGJIAGANG FREE TRADE ZONE KANGDE FILM
INDUSTRY CO.,LTD. BEIJING BRANCH
No.26, Zhenxing Road, Changping District,
Beijing, CHINA 102200
Tel: 86-10-8228 2777
sales@kdxfilm.com
www.kdxfilm.com.cn

ZHANGJIAGANG FREE TRADE ZONE KANGDE FILM
INDUSTRY CO.,LTD.
West of Taiwan Road, Zhangjiagang Free Trade Zone,
Jiangsu, China
TEL:+86-0512-58329502
sales@kdxfilm.com

KDX AMERICA

8880 Mistletoe Dr. Easton,
MD 21601
877-492-9210 (Toll Free)
Tel: 1-877-492-9210 (Toll Free)
sales@kdxamerica.com
www.kdxamerica.com

KDX EUROPE

De Koumen 78,6433 KE
Hoensbroek,
The Netherlands
Tel: +31 (0) 45 546 6106
info@kdx europe.com
www.kdx europe.com